

3. IMPREGNATING RESINS **VUDAC/** Polyesterimide in diacrylate/ **1K-NAH 99/800/Z**



CABLES



IMPREGNANTS



WIRES



RESEARCH

Application:

Impregnating resins are suitable for trickling impregnation of high mechanical stressed windings of electrical rotating machines for starters alternators and tools.

Characteristics:

Impregnating trickle resin resins 1K-NAH 99/800Z features with short curing time at 140°C. It is one component unsaturated polyesterimide resin in diacrylate. Only a small amount of volatile substances avoid during curing. It is resistant to vapor solvents, oils and refrigerator liquids.

Processing data and properties of liquid resin:

Density (DIN 53 217)	20 °C	[kg/m ³]	1050-1150
Viscosity	25 °C	[mPa.s]	700-1000
Shelf- life	5- 23 °C	[months]	min. 4
Flash point (Cleveland)		[°C]	>112
Gel-time ¹	130 °C	[min]	2-4
Reaction time ^{2,3}	130 °C	[min.]	
Maximum temperature ^{2,3}	100 °C	[°C]	200-220
Curing time ⁴	130 °C 140 °C	[min]	15-30 10-15
Effect of resin on enamelled wires ⁵			OK



F-11.1.22-04-2/11en

3. IMPREGNATING RESINS **VUDAC/** Polyesterimide in diacrylate/ **1K-NAH 99/800/Z**



CABLES



IMPREGNANTS



WIRES



RESEARCH

Properties after cure:

Curing of test specimen	130 °C	[h]	2
Ability to cure in considerable thickness ^{2,6}		[degree ¹⁰]	S 1 U 1 I 1.1
Electric strength ^{2,7}	23 °C 155 °C after 96 h in 92% humidity at 23 °C	[kV/mm]	80-100 60-80 40-60
Volume resistivity ²	23 °C 155 °C after immersion in water for 96 h at 23 °C	[Ω.m]	10 ¹⁴ 10 ⁹ 10 ¹³
Twisted coil test ⁸	23 °C 180 °C	[N]	250-350 100-120
Thermal endurance ⁹		[°C]	183

1. DIN 16 945 Method A

2. DIN 46 448 Blatt 1

3. Fe-Ko after ASTM D 2471-71

4. from reached temperature 130 °C in winding

5. STN 67 31 50 part. 11, met. B after 60 min at 60 °C

6. 2 h at 100 °C + 2 h at 130 °C

7. Test specimens A2, cylindrical electrode ø6 mm

8. IEC 61033 met. A,

9. IEC 60216-1,-2

10. S – smooth

The underside: U - non tacky

The interior: I – hard, free of bubbles

11. UL test 1446 File E233982

Packing a storage:

Impregnating resin is delivered in drums. It has to be stored in tightly closed drums at temperature from +5 °C to +25 °C.

In terms of traffic regulations impregnating resins are not classified as hazardous product.

The information provided herein accords with our knowledges about the subject on the date of publication. This information might be revised if new knowledges and experience will be available. The data provided fall within the normal range of product properties are related only to the specific material. These data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to set limits or used alone as the basis for design. The data are not intended for substitute of any testing that you might need to do for decision if the specific material is suitable for your particular purposes. Since VUKI ca not anticipate all variants in actual end-use conditions, VUKI makes no warranties and assumes no liability in connection with any use of this information. Nothing in this document is to be considered as a license to application or recommendation to infringe any patent rights.

F-11.1.22-04-2/11en



VUKI
SINCE 1950