

2. IMPREGNATING RESINS VUDAP/ Polyesterimide in diallylphthalate/ NH 91/Z, NH 91 LV/Z



CABLES



IMPREGNANTS



WIRES



RESEARCH



Application:

Impregnating resins NH 91/Z and NH 91 LV/Z are suitable for trickling impregnation method for impregnation of high temperature stressed windings of stators and rotors of high speed electrical machines for domestic appliances and hand tools up to thermal class H according to IEC - Publication 216.

Windings impregnated with impregnating resins NH 91/Z and NH 91 LV/Z provide good reliability of machines in reversing operation, good resistance to tropical climates, and good resistance to solvents, acids, oils, freons and radioactivity

Description:

Chemical base of one – component impregnating resins is modified unsaturated polyester resin diluted in diallylphthalate. They are typical for their short cure time 140 °C.

Processing data:

			NH 91/Z	NH 91 LV/Z
Density (DIN 53 217)	20°C	[kg/m ³]	1130 – 1160	1120 - 1140
Flow time: DIN cup 4 ISO cup 6	25°C	[s]	110 – 150 75 - 110	50 - 80 35 - 60
Shelf- life	max. 25°C	[months]	6	6
Flash point STN EN 22592		[°C]	>145	>145
Reaction time	100°C	[min]	7 - 12	7 - 12
Gel-time ¹	100°C 130°C	[min]	6 - 11 1,5 – 3	6 - 11 1,5 - 3
Exothermal temperature ^{2,3}	100°C	[°C]	210 - 240	210 - 240
Cure time ⁴	130°C 140°C	[min]	15 – 30 10 - 15	15 – 30 10 - 15
Effect of varnish on enameled wires ⁵ (IEC 317 – 3, -8, -13)			suitable	suitable

Polyesterimide in diallylphthalate



F-11.1.22-12-2/11en

2. IMPREGNATING RESINS VUDAP/ Polyesterimide in diallylphthalate/ NH 91/Z, NH 91 LV/Z



CABLES



IMPREGNANTS



WIRES



RESEARCH

Properties after cure:

			NH 91/Z	NH 91LV/Z
Ability to cure in considerable thickness ^{2,6}			1.1.1.1. ¹⁰ 0.1.1.1.	1.1.1.1. ¹⁰ 0.1.1.1.
Curing time of test specimen	130°C	[h]	2	2
Dielectric strength ^{2,7}	23°C	[kV/mm]	120 – 140	120 – 140
	after immersion in water for 24 hrs		40 - 60	40 - 60
Volume resistivity ²	23°C	[Ω.m]	10 ¹⁴	10 ¹⁴
	180°C after immersion in water for 96 hrs		10 ⁹ 10 ¹³	10 ⁹ 10 ¹³
Twisted coil test ⁸	23°C	[N]	250 – 350	250-300
	180°C		100 - 120	100 - 120
Thermal endurance ^{9,10} , Test criterion:		[°C]	183	183

1. DIN 16 945 Method A

2. IEC 464 48 Blatt 1

3. Fe-Ko thermoelement according to ASTM D 2471-71

4. after the winding has reached 130 (140)°C

5. STN 67 31 50 art.11 met. B after 60 min. at 60°C

6. 1 h at 100°C+2h at 130°C

7. Test specimen A2, cylindrical electrode fi 6mm

8. IEC 61033 met. A

9. IEC 60216

10. UL E file 233982

Packing a storage:

Impregnating resins are delivered in 25 kg drums. They have to be stored in tightly closed drums at temperature max. +25 °C.



VUKI
SINCE 1950

The information provided herein accords with our knowledges about the subject on the date of publication. This information might be revised if new knowledges and experience will be available. The data provided fall within the normal range of product properties are related only to the specific material. These data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to set limits or used alone as the basis for design. The data are not intended for substitute of any testing that you might need to do for decision if the specific material is suitable for your particular purposes. Since VUKI ca not anticipate all variants in actual end-use conditions, VUKI makes no warranties and assumes no liability in connection with any use of this information. Nothing in this document is to be considered as a license to application or recommendation to infringe any patent rights.

F-11.1.22-12-2/11en